

**➤ Klebstoff-Film Ultra**

stark/stark haftend

SPRINTIS Schenk GmbH & Co. KG  
Ludwig-Weis-Str. 11 · D-97082 Würzburg  
Tel. +49(0) 931 / 40 41 6-240 · Fax: -100

[www.sprintis.de](http://www.sprintis.de) · [info@sprintis.de](mailto:info@sprintis.de)

01/2019

**Anwendungsbeispiele**

Gut geeignet für die Verwendung auf Karton, Broschüren und auf jedem Gewebe, um schwierige Anwendungsoberflächen zu verkleben. Kompatibel mit unserem ATG900 und allen Arten von Spendern auf dem Markt mit ATG-System.

**Eigenschaften**

Kleberart	Lösungsmittel Acrylat
Trägermaterial	Glasfaser
Dicke (Kleber & Träger)	0.13 mm
Klebekraft	28 +/- 2 N/25mm
Abdeckung Material	Silikonpapier
Abdeckung Farbe	Braun (havanna)
Temperaturbereich von/bis	-40° bis +120° C
Lebensmittelkontakt	Indirekt (level 2)

**Lagerempfehlung / Lagerzeit**

Bei üblichen Lagerbedingungen bei Raumklima (ca. 50% relative Luftfeuchte & ca. 20°C Raumtemperatur) besitzt das Produkt in Originalverpackung eine Lagerzeit von mindestens 12 Monaten nach Eingang beim Kunden.

**Hinweis:**

Die technischen Angaben geben wir Ihnen nach bestem Wissen, jedoch unverbindlich. Aufgrund der vielfältigen material- und umgebungsbedingten Einflüsse empfehlen wir vor jedem Gebrauch eine Eignungsprüfung an Originalmaterialien. Bitte beachten Sie dabei auch die für die Haftklebebänder üblichen Verarbeitungsbedingungen.

**Adhesive film Ultra**

strong/strong adhesive

SPRINTIS Schenk GmbH & Co. KG  
Ludwig-Weis-Str. 11 · D-97082 Würzburg  
Tel. +49(0) 931 / 40 41 6-240 · Fax: -100

[www.sprintis.eu](http://www.sprintis.eu) · [info@sprintis.eu](mailto:info@sprintis.eu)

12/2023

**Applications & purposes**

Recommended for general purpose applications in the paper industry, samples, leather, fabrics, tissue, cardboard, bricolage, foam, etc.  
Good initial tack and excellent adhesion on irregular surfaces.

**Characteristics**

Adhesive type	modified solvent acrylic
Carrier material	fibers glass
Thickness (adhesive & carrier)	0.13 mm
Peel adhesion, adhesive strength	15 +/- 2 N/25mm
Release liner material	Silicon paper
Release liner colour	Brown
Temperature from/to	-40° to +120°C
Food contact	Indirect (level 2)

**Storage recommendation / Shelf life**

Under normal storage conditions in a room climate (approx. 50% relative humidity & approx. 20°C room temperature) the product in its original packaging has a storage period of at least 12 months after receipt by the customer.

**Disclaimer:**

Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third part. We cannot assume any liability for the use of our products in conjunction with other materials.